

<<水工混凝土配合比设计规程>>

图书基本信息

书名：<<水工混凝土配合比设计规程>>

13位ISBN编号：9787508379852

10位ISBN编号：7508379853

出版时间：2009-1

出版时间：中国电力出版社

作者：中华人民共和国国家发展和改革委员会

页数：39

字数：35000

版权说明：本站所提供下载的PDF图书仅提供预览和简介，请支持正版图书。

更多资源请访问：<http://www.tushu007.com>

<<水工混凝土配合比设计规程>>

内容概要

During the compiling process, this Standard not only absorb some relevant contents in the similar domestic and international standards that are suitable for the application of hydraulic concrete in China, but also emphasizes the characteristics of mass hydraulic concrete. With the advancement of hydraulic concrete technology, the use of admixtures and additives has become more and more popular, and widespread attentions have been paid to the durability of concrete. Therefore, changes of stipulations in this Standard are more focused on the use of admixtures, and additives and the durability of concrete.

<<水工混凝土配合比设计规程>>

书籍目录

Foreword1 Scope2 Normative References3 Terms and Symbols 3.1 Terms 3.2 Symbols4 General5
Determination of Required Average Compressive Strength6 Selection of Basic Parameters for Mix Design 6.1
Water-cementitious material ratio 6.2 Water Content 6.3 Aggregate Gradation and Sand Ratio 6.4 Admixture
and Additive Content7 Calculation of Concrete Mix Proportion8 Trial Mixing, Adjustment and Determination of
Concrete Mix Proportion 8.1 Trial Mixing 8.2 Adjustment 8.3 Determination9 Mix Design of Special
Concrete10 Mix Design of Hydraulic Mortar 10.1 Basic Principles of Mortar Mix Design 10.2 Determination
of Required Average Compressive Strength 10.3 Calculation of Mortar Mix Proportion 10.4 Trial Mixing,
Adjustment and Determination of Mortar Mix Proportion

<<水工混凝土配合比设计规程>>

章节摘录

6 Selection of Basic Parameters for Mix Design

6.1 water-cementitious material ratio

6.1.1 The water-cementitious material ratio shall be determined by test according to the design requirements for the concrete strength, and shall comply with the stipulations in DL/T 5144.

6.1.2 The water-cementitious material ratio shall also meet the design requirements of impermeability and frost resistance grade. The impermeability and frost resistance grades are related to types of cement, water-cementitious material ratio, types and contents of admixtures and additives, curing age and so on. For the large and medium projects, the relevant curve shall be established by test and the water-cementitious material ratio should be determined according to the test result and meet the requirements of the designed technical indices. If test data are not available, the water-cementitious material ratio for anti-freezing concrete should be determined according to the stipulations in DL / T 5082, based on frost resistance grade and the maximum aggregate size.

6.1.3 For the concrete mixed with additives, the maximum water-cementitious material ratio shall be lowered appropriately and determined by test.

<<水工混凝土配合比设计规程>>

编辑推荐

《水工混凝土配合比设计规程(DL/T 5330-2005)》由中国电力出版社出版。

<<水工混凝土配合比设计规程>>

版权说明

本站所提供下载的PDF图书仅提供预览和简介，请支持正版图书。

更多资源请访问:<http://www.tushu007.com>