

<<DL/T 5193-2004 环氧树>>

图书基本信息

书名：<<DL/T 5193-2004 环氧树脂砂浆技术规程 (英文版) >>

13位ISBN编号：9787508381534

10位ISBN编号：750838153X

出版时间：2009-3

出版单位：中国电力出版社

作者：中华人民共和国国家发展和改革委员会发布

页数：88

字数：73000

版权说明：本站所提供下载的PDF图书仅提供预览和简介，请支持正版图书。

更多资源请访问：<http://www.tushu007.com>

<<DL/T 5193-2004 环氧树>>

前言

This Specification IS revised on the demands of the Document No.22[2000]entitled"Notice about approving the scheme on formulatng or revising the sector standards of the electric power industry in1999"issued by the State Economic and Trade Commission . This Specification specifies the quality requirements andperformance test methods of raw materials for epoxy resin mortar,performance tests and construction technologies of epoxy resinmortar . Due to its characteristics of high strength and excellentcomprehensive performance,epoxy resin mortar has been used asanti-scouring and anti-abrasion protective cover of flow surface ofhydraulic concrete and as a mending and consolidation material forthe locations damaged by scouring,abrasion and cavitation erosion inthe past 40 years . It has also been used as a mending andconsolidation material for industrial and civil buildings,highways,bridges and airport runways,etc..The quantity and application scope of epoxy resin mortar have been increased continuously with development of epoxy resin material and improvement of constructiontechnologies in recent years . However,there is no related technical specification for a long time,which has hindered the application andtechnology development of epoxy resin mortar as no technical requirement is available for epoxy material processing,performancetest and on-site construction . So it is very necessary to develop a specification for epoxy resin mortar that is suitable for our country,in order to standardize the research and application of epoxy resin .

<<DL/T 5193-2004 环氧树>>

内容概要

本书为DL/T 5193《环氧树脂砂浆技术规程》的英文版，规定了环氧树脂是将原材料的基本性能要求及其检测方法、质量控制等内容。

<<DL/T 5193-2004 环氧树>>

书籍目录

Foreword1 Scope2 Normative References3 Terms and Symbols 3.1 Terms and Definitions 3.2 Symbols4
Quality Requirements and Methods of Performance Tests for Raw Materials of Epoxy Resin Mortar 4.1 Quality
Requirements for Raw Materials 4.2 Performance Tests for Raw Materials5 Performance Tests of Epoxy Resin
Mortar 5.1 Preparation of the Mixture 5.2 Molding Method of Test Specimen 5.3 Consistency Test of
Epoxy Resin Mortar 5.4 Tests of Pot Life and Curing Age of Epoxy Resin Mortar 5.5 Apparent Density Test
of Epoxy Resin Mortar 5.6 Test and Classification of Exothermic Peak Temperature of Epoxy Resin Mortar
5.7 Linear Shrinkage Test of Epoxy Resin Mortar 5.8 Thermal Compatibility between Epoxy Resin Mortar
Coating and Concrete 5.9 Compressive Strength Test of Epoxy Resin Mortar 5.10 Tensile Strength Test of
Epoxy Resin Mortar 5.11 Flexural Strength Test of Epoxy Resin Mortar 5.12 Test Method for Bond Tensile
Strength of Epoxy Resin Mortar to Cement Mortar 5.13 Test Method for Bond Tensile Strength of Epoxy Resin
Mortar to Concrete 5.14 Test Method for Compressive Elastic Modulus of Epoxy Resin Mortar 5.15 Test of
Linear Expansion Coefficient of Epoxy Resin Mortar 5.16 Test of Medium-resistance Performance of Epoxy
Resin Mortar 5.17 Aging Test of Epoxy Resin Mortar 5.18 Test Method of Impact-resistant Performance of
Epoxy Resin Mortar 5.19 Test Method of Abrasion Resistant Performance of Epoxy Resin Mortar Against Silt
Laden Water 5.20 Testing Method of Anti-seepage Performance of Epoxy Resin Mortar6 Construction
Technologies 6.1 Construction Preparation 6.2 Construction Procedure 6.3 Treatment of Substrate
Concrete 6.4 Mixing Techniques and Requirements 6.5 Brushing Techniques and Technical Requirements
6.6 Quality Check, Control and Test 6.7 Curing of Epoxy Mortar Coat 6.8 Construction Safety and Labor
ProtectionAnnex A (Normative) Testing and Classification of Exothermic Peak TemperatureAnnex B
(Normative) Test Method of Bonding Tension Strength

<<DL/T 5193-2004 环氧树>>

章节摘录

5.1.1 Scope It is applicable to preparation of epoxy resin mortar mixture . 5.1.2 Requirements 1 The test material or mixtures shall be remained at the temperature of 23 ± 2 for at least 24 h . 2 It is recommended to directly use half-ready epoxy resin mortar packaged in proportion and provided by suppliers . When use bulk materials , the components shall not be less than 10 g , to the nearest ± 0.05 g . 3 The sequences of adding the materials shall follow supplier's indication . Mix until the color of the mixture becomes uniform (or follow supplier's indication) , and avoid exotherm reaction caused by over-mixing . 4 Protective clothes and latex (or plastic) gloves shall be worn during the process to avoid direct contact with chemicals . In case that the mixture gets on the skin , wipe it off with dry cloth or tissue immediately , and then wash the affected skin with soap and water . Do not wipe the affected part with solvent fluids because it accelerates hazardous substances permeating into skin . 5.1.3 Instruments . 1 Bench Scale : its capacity is 5 kg , and sensitivity is 1 g . 2 Balance : its capacity is 500 g . and sensitivity is 0.01 g . 3 Mixing equipments : from small-size mixer to low-speed .

<<DL/T 5193-2004 环氧树>>

版权说明

本站所提供下载的PDF图书仅提供预览和简介，请支持正版图书。

更多资源请访问:<http://www.tushu007.com>