

<<建工英语-教师用书>>

图书基本信息

书名：<<建工英语-教师用书>>

13位ISBN编号：9787544616119

10位ISBN编号：7544616118

出版时间：2010-1

出版时间：上海外语教育出版社

作者：（德）赫拉茨 编，郑峻 编译

页数：38

版权说明：本站所提供下载的PDF图书仅提供预览和简介，请支持正版图书。

更多资源请访问：<http://www.tushu007.com>

## <<建工英语-教师用书>>

### 内容概要

《新理念中职职业英语系列教材》由上海外语教育出版社整合国际先进中职职业英语教学资源编译出版而成，为我国中职职业英语教学的发展提供了国际领先的教学材料。

系列教材首批推出3个分册：《汽车英语》、《宾馆英语》和《建工英语》，每个分册都由学生用书、教师用书和配套录音组成。

课堂指导 / 教师用书含有以下内容：教学安排建议、所有练习的参考答案、听力练习录音文字、练习题、测试题。

<<建工英语-教师用书>>

书籍目录

A 编写说明B 参考答案及教学提示 Unit 1 Unit 2 Unit 3 Unit 4 Unit 5 Unit 6 Unit 7 Unit 8 Unit 9 Unit 10  
Unit 11 Unit 12 Unit 13 Unit 14 Unit 15 Unit 16 Unit 17 Unit 18 Unit 19 Unit 20C 练习题 1  
: Understandingjob adverts 2 : Applying for ajob 3 : Y0urcurriculum vitaeD 测试题 试卷1 试卷2 参考答案

## 章节摘录

A Now... over here we have cement mortar which is mixed in the ratio of one part cement and four parts sand. It is an extremely firm and strong mortar. The problem is that cement mortar shrinks a lot once it has dried.

B So, let's look at gauged mortar now. This can be mixed in different ways. One typical mixture is one part cement, eight parts sand and two parts lime. This type of mortar is easy to work with and has a short drying time. It is a firm and strong mortar.

C Over here we have lime mortar. This is mixed one part lime to three parts sand. It is easy to work with — that's because of the lime content. However — and here's the disadvantage — it has a long drying time and is less firm than other types of mortar.

D And so, this one here is another gauged mortar mix. It is made of one part cement, six parts sand and one part lime. Like other gauged mortar mixes it dries quickly and is really strong.

A cement mortar : cement 1 part, sand 4 parts. B gauged mortar ( 1 ) ; cement 1 part, sand 8 parts, lime 2 parts. C lime mortar; lime 1 part, sand 3 parts.

D gauged mortar ( 2 ) ; cement 1 part, sand 6 parts, lime 1 part.

<<建工英语-教师用书>>

版权说明

本站所提供下载的PDF图书仅提供预览和简介，请支持正版图书。

更多资源请访问:<http://www.tushu007.com>